



# Technical Data Sheet

## B2002 Aluminium Epoxy Stick

### PRODUCT DESCRIPTION

B2002 is a hand kneadable, Specialty Epoxy Putty that mixes in one minute to provide fast, permanent repairs to most Aluminium surfaces. When applying B2002 to surfaces it is necessary to work the material forcefully into the surface and apply pressure until adhesion begins to take effect. The lower the temperature the longer it takes to cure. It comes in a handy rod form with the curing agent encapsulated in the contrasting colour base material. Its putty-like consistency eliminates drips and runs, providing "no mess" application with no tools required to use. The mixed epoxy turns from a silvery colour to "Alloy" upon curing and will not yellow upon exposure to UV light. After final cure, B2002 may be drilled, sawed, tapped, filed, sanded and painted. It allows patching in areas where welding is impossible.

### APPLICATIONS

After proper mixing, B2002 molds like clay and may be used to permanently patch dents, scratches, cuts, gouges and holes in items such as housings and all types of repairs to moldings and injection type shapes. B2002 is ideal for making emergency repairs to reforming, rebuilding and patching anything made out of aluminium such as HVAC parts, refrigeration units, air conditioning units, machine parts, alu-roofing and siding, flagpoles, shelving, platforms, walkways, campers, road vehicles, canopies, gutters, truck and trailer bodies, wheels, manifolds, stripped threads, marine hardware and casings.

### USEFUL HINTS/NOTES

Mixing: Twist or cut off required amount. To mix, knead with fingers to a uniform colour. If mixing is difficult, warm B2002 to room temperature or slightly above. Apply to the surface to be

repaired (within 2 minutes of mixing). The mixed epoxy does not exhibit high bond strength at this point, but appears to be merely lying on the surface. Force into any cracks or holes to be filled and strike off excess material, preferably with a tool wetted with clean water. Work the material forcefully into the surface and apply pressure until adhesion begins to take effect.

For a smooth appearance of the cured compound, hand rub with water or a damp cloth prior to hardening. Remove excess material before hardening begins. After 15-20 minutes the epoxy will harden like metal and start to form a tenacious bond. After just 45 minutes B2002 is completely cured and can be drilled, sawed, carved, sanded, stained or painted.

### INSTRUCTIONS FOR USE

In order to achieve optimum adhesion, surface should be cleaned free of grease or dirt. Scuffing or sanding the surface prior to cleaning helps to ensure a good bond.

### TECHNICAL FEATURES

Resin	Light Silver
Epoxy Resistance	Hydrocarbons, ketones, esters, halo-carbons, alcohols, aqueous salt solutions, diute acids and bases
Electrical Resistance	30,000 mega Ohms
Dielectric Strength (steel)	300 Volts/mil
Shrinkage	<1%
Non Volatile Content	100%
Shelf Life	24 months @ 24°C



# Technical Data Sheet

## B2002 Aluminium Epoxy Stick

**CURED PERFORMANCE**

Initial Cure	1 hour
Full Cure Time	24 hours
Lap Shear Strength (Steel)	4.8 N/mm <sup>2</sup>
Shore D Hardness	70/80
Compressive Strength	84N/mm <sup>2</sup> - 12,000 psi

**PROPERTIES**

Opening Time	5 mins
Max Temp Resistance	121°C Continuous 149°C Intermittent

**STORAGE**

Store in cool conditions, preferably away from direct sunlight or excessive heat. Shelf life at least 24 months @ 24°C.

**HEALTH & SAFETY**

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

**PACKAGING FORMAT**

Tubes.....50g, 114g  
Clam.....50g

**PRODUCT DISCLAIMER**

Bondloc offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bondloc's research only. Since the conditions and methods of use of the products are beyond our control, Bondloc expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BONDLOC'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bondloc does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

