



Issue no. 5 May 20

RA 1312 INTERLEAVED 30 MICRON ALUMINIUM TAPE, ACRYLIC ADHESIVE

<u>TECHNICAL DETAILS</u>	<u>TYPICAL VALUE</u>	<u>UNITS</u>
Thickness, foil carrier plus adhesive	0.07	mm
Foil thickness	Level 3	
Adhesive type	Acrylic	
Release liner weight	62	g/sq.m.
Peel adhesion	400	N/m
Polyester Loop Tack	800	N/m
Tensile strength	1500	N/m
Elongation at break	3	%
Service temperature range	-40 to +120	Deg. C.
Recommended application temperature rang	5 to 25	Deg. C.
Moisture vapour permeability	Less than 1	g per sq. m., 24h at 40 deg C., 90% R.H.
Shear adhesion, 1Kg @23 deg. C.	60	Hours
Shelf life	12	Months
Flame retardancy: Class 'O' rated when tested to BS476 0n foil-faced insulation panels		
Test Methods: BS 3924:1978		

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR

PSA Solutions Ltd, Unit 3 Amos Lodge, Ashby Road, Ullesthorpe LE17 5DN

Tel 01162 865141 Email sales@psasolutions.uk.com