



Product datasheet Issue No 1 Issued Oct 17

## RA 2556 DOUBLE-SIDED HIGH TACK TISSUE TAPE Increased coat weight

<u>TECHNICAL DETAILS</u>	<u>TYPICAL VALUE</u>	<u>UNITS</u>
Adhesive Type	Pressure Sensitive Hot-Melt Rubber Resin	
Thickness, adhesive + carrier	0.110	mm
Release liner thickness	0.055	mm
180 degree peel adhesion:		
Open side	1150	N/m
Closed side	1150	N/m
Polyester loop tack:		
Open side	1050	N/m
Closed side	1050	N/m
Liner release	15	N/m
Tensile strength	1000	N/m
Elongation at break	4	%
Service temperature	-40 to +60	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	> 50	Hours
Shelf life	12	Months
Test Methods: BS 7116		
Standard fingerlift formats	6/12, 9/15, 12/18, 18/24, 24/30 Other formats, inc. offset fingerlift available subject to min. quantities	
<small>THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY. ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.</small>		

PSA Solutions Ltd Unit 3 Amos Lodge, Ashby Road, Ullesthorpe LE17 5DN  
Tel: +44 (0)1162 865141 Email: sales@psasolutions.uk.com