Product datasheet Issue No 2 Issued May 20

PSA2991F DOUBLE-SIDED POLYESTER FILM - BOX SEAL TAPE

White Glassine Release Liner

TECHNICAL DETAILS		TYPICAL VALUE	UNITS
Adhesive Type : Pressure Sensitive Hot Melt / Rubber Resin			
Thickness, adhesive + carrier		0.210	mm
Release liner thickness		0.080	mm
180 degree peel adhesion:	Open side	1000	N/m
	Closed side	1400	N/m
24 Hour Dwell	Open side	1600	N/m
	Closed Side	2400	N/m
Polyester loop tack:	Open side	1100	N/m
	Closed side	1400	N/m
Liner release		90	GSM
Tensile strength		4600	N/m
Elongation at break		120	%
Service temperature		-10 T0 +60	Deg. C.
Recommended application temperature		+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		>24	Hours
Shelf life		12	Months

Test Methods: BS 7116

The individual ingredients of the the adhesive have been tested and approved for indirect food contact to the FDA specification 175.105

**THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.**

PSA SOLUTIONS LIMITED UNIT 3 AMOS LODGE, ASHBY ROAD, ULLESTHORPE LE17 5DN
TEL: 01162865141 EMAIL: sales@psasolutions.uk.com